



Excellent tear-resistant protection and superior solar control with 3M™ Scotchshield™ Safety & Security Window Film Ultra Prestige Series.

- ▶ Combines the benefits of 3M™ Ultra Series with the benefits of 3M™ Prestige Series Window Film
- ▶ Tear resistant glass fragment retention film for increased protection of people, property and possessions
- ▶ Can be combined with 3M™ Impact Protection Attachment System for additional safety and security
- ▶ High visual light transmission providing excellent aesthetics
- ▶ Up to 97% infrared rejection providing energy savings and enhanced comfort*
- ▶ Low interior and exterior reflectivity enhances views while maintaining exterior appearance
- ▶ Helps extend the life of furnishings by significantly reducing harmful UV rays, the largest cause of fading
- ▶ Comprehensive warranty from 3M

| | |
|----------------------------|-------|
| Break and Entry | ★★★★★ |
| Safety Glazing | ★★★★★ |
| Seismic | ★★★★★ |
| Blast Mitigation | ★★★★★ |
| Visible Light Transmission | ★★★★★ |
| Low Reflection | ★★★★★ |
| Infrared Rejection | ★★★★★ |

Best ★★★★★

Better ★★★★☆

Good ★★★☆☆

Fair ★★☆☆☆

Not Recommended ★☆☆☆☆

In comparison to other 3M™ Safety & Security Window Films

*IR Rejection as measured from 900–1000nm

Ultimate protection and clarity.





Break and Entry

- ▶ Provides precious time by helping to deter unwanted individuals from entering your building or home
- ▶ Help protect occupants and assets

Completed Testing — Ultra S600

- ▶ EN 356
- ▶ Independently evaluated, contact 3M for details



Safety Glazing and Human Impact

- ▶ Upgrade your glass to meet safety glazing codes*
- ▶ Help protect your occupants from broken glass hazards

Completed Testing

- ▶ ANSI Z97.1
- ▶ EN 12600
- ▶ 16 CFR CPSC 1201







Bomb Blast and Explosion Protection

- ▶ Help protect people from flying glass shards, one of the most common causes of blast related injuries and fatalities

Completed Testing

- ▶ ASTM F1642
- ▶ GSA TS01-2003

Product Performance and Technical Data

| Glass Type (All 1/4") | Film Type | Visible Light | | | Total Solar Energy Rejected | Solar Heat Gain Coefficient (G Value) | U Value | | Solar Heat Reduction | UV Light Rejected | Glare Reduction | Visible Light to Solar Heat Gain Ratio |
|---|--------------|-------------------------|-------------------------|-------------|-----------------------------------|--|---------------|-----------|-------------------------|----------------------|--------------------|--|
| | | Reflected (Interior) | Reflected (Exterior) | Transmitted | | | btu/ hft²F | w/ m²K | | | | |
|  Clear | Ultra PR S70 | 9% | 10% | 68% | 50% | 0.51 | 1.02 | 5.8 | 38% | 99.9% | 23% | 1.4 |
| | Ultra PR S50 | 7% | 9% | 48% | 56% | 0.44 | 1.02 | 5.8 | 46% | 99.9% | 46% | 1.1 |
|  Tinted | Ultra PR S70 | 8% | 6% | 41% | 56% | 0.44 | 1.02 | 5.8 | 30% | 99.9% | 23% | 0.9 |
| | Ultra PR S50 | 7% | 6% | 29% | 60% | 0.40 | 1.02 | 5.8 | 37% | 99.9% | 45% | 0.7 |
|  Double Clear | Ultra PR S70 | 13% | 16% | 61% | 44% | 0.56 | 0.47 | 2.7 | 20% | 99.9% | 23% | 1.1 |
| | Ultra PR S50 | 9% | 15% | 43% | 47% | 0.53 | 0.47 | 2.7 | 25% | 99.9% | 46% | 0.8 |
|  Double Tinted | Ultra PR S70 | 12% | 9% | 37% | 58% | 0.42 | 0.47 | 2.7 | 17% | 99.9% | 23% | 0.9 |
| | Ultra PR S50 | 9% | 9% | 26% | 60% | 0.40 | 0.47 | 2.7 | 21% | 99.9% | 46% | 0.6 |

3M products are tested to multiple industry standards. Glazing systems vary. Contact 3M for more information.

*Building codes vary, please consult with 3M and your local code official.

Film Properties (nominal)

Note: The following technical information and data are based upon limited 3M testing conditions and should not be used for specification purposes.

| Film Type | Film Thickness | Construction | Tear Resistance | Tensile Strength | Break Strength | Elongation at Break | Peel Strength | Abrasion Resistance |
|----------------|--------------------|---------------|-----------------|-------------------------|----------------------------|---------------------|---------------------------|---------------------|
| Ultra Prestige | 8 mil (0.22 mm) | Micro-layered | 1,100 lbs% | 27,000 psi (186 MPa) | 215 lbs/in (956 N/25mm) | 120% | > 4 lbs/in (18 N/25mm) | <3% Δ Haze |

Warranty, Limited Remedy and Disclaimer: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. **3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.** If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. **Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Renewable Energy Division
3M Center, Building 235-2S-27
St. Paul, MN 55144-1000
3M.com/windowfilm

3M is a trademark of 3M.
Used under license in Canada.

Please recycle. Printed in the U.S.A.
© 3M 2016. All rights reserved.
98-0150-0755-6